

**In The Specification:**

Please amend the specification as follows:

Please replace the paragraph on page 55, lines 5-18 with the following replacement paragraph:

<b><u>Component</u></b>	<b><u>Example 52 53</u></b>	<b><u>Example 53 54</u></b>
UNIFLEX 312	1 part	1 part
WITCO Mark V1923	0.04 parts	0.04 parts
UVINOL 400	0.13 parts	0.13 parts
TINUVIN 292	0.04 parts	0.04 parts
EB Acetate	44.9 parts	44.9 parts
DPM Acetate	25 parts	25 parts
20 weight percent ACRYLOID A-11 in EB Acetate	6.91 parts	6.91 parts
Black Paste	21.68 parts	21.68 parts
(30% MICROLITH C-K black pigment chip in EB Acetate)		
FLUORAD FC-430	0.25 parts	0 parts
AF 9000	0.05 parts	0 parts
Surfactant 3	0 parts	0.1 parts